

B03

Gloss converter



Gloss converter is an addition to **Kar-Bon** base system.

Thanks to its application, we can get a satin, scratch-resistant surface.

There is no need to apply the clear varnish on the top. The base varnish associated with this additive is very well suited for universal use, e.g. for painting the engine compartment.

Paint fluidity:	●●●●●
Gloss:	●●●○○
Resistance to scratches:	●●●○○
Plastic adhesion:	●●●○○
Adhesion :	●●●●●

Unit	Packaging	Collective (box)
1 L		3 pcs



100 parts of Kar-Bon,
30 parts of converter B03,
25 parts of thinner CP 048.



Two or three full layers or until full coverage is achieved.
 Spray gun*. Gravity nozzle: **1.2-1.4 mm**. Suction nozzle: **1.4-1.6 mm**.
 Operating pressure - high pressure: **3- 4 bar***; HVL P: **2 bar***.

* Use high pressure equipment and HVL P Pressure as recommended by the gun manufacturer.



Evaporation before applying consecutive layers: **5 min.**



Drying time 20°C, 65% H.R:
 Dust free: **5 min**
 Air dry: **10-15 min**
 Through dry: **15-25 min***

* The drying time may change depending on the number of layers and the selected color.

Surface preparation:

Clean surfaces with silicon remover. Matt the old coatings.

Spray viscosity in 20°C:

~17-19 s DIN Cup 4 mm

Recommended sizes of paint strainers:

125-190 µm

VOC:

2004/42/WE/II B(e)(840)<840

Date of minimum durability:

24 months (in the original unopened package)

Check out our "Kar-Bon" products on page 8.

The recipe of the product complies with the VOC guidelines. The products supplied by our company are subject to a number of factory tests, so they can meet the highest demands. However, be aware of the individual conditions of storage, preparation and applications that can influence on the effect of varnishing. The guarantee to keep the highest quality of the coating is to use the product only with the products of the Manufacturer and in accordance with the recommendations of the Manufacturer. The Manufacturer does not guarantee performance and compatibility of the Products with products other than those of the Manufacturer. In order to recognize the guarantee and all claims, the user shall use the technologies and techniques for given Products - according to the technical data sheet and execute the sample spray prior to target painting.