PROFIX



CP 325 UBS

Stone chip and underbody protection

CP 325 UBS is meant for protecting the bottom part of a car body, as well as the front and rear moulding, side sills, bumpers and doors.

The product has soundproof properties. With its elasticity, it protects the car from the consequences of being hit by rocks and protects it from rust and salt.

UBS can be coated (no change in color).

Unit	Packaging Collective (box)	Available colors
1 kg	12 pcs	



Shake well before using.



Apply two or three layers and leave to dry for about **10 min** for each layer. Apply two, three layers with a high-density pulp gun. Nozzle opening with the pneumatic method: **3-4 mm**.

Working pressure: 1-4 bar.

Top coat should be application after ~1 h.



Evaporation before applying consecutive layers: 5-10 min.



Drying time 20°C, 65% H.R: **60-90 min**.



After partial painting just put the cap to allow its use in the future.

The recipe of the product complies with the VOC guidelines. The products supplied by our company are subject to a number of factory tests, so they can meet the highest demands. However, be aware of the individual conditions of storage, preparation and applications that can influence on the effect of varishing. The guarantee to keep the highest quality of the coating is to use the product only with the products of the Manufacturer and in accordance with the recommendations of the Manufacturer (no even to even the performance and compatibility of the Products with products other than those of the Manufacturer. In order to recognize the guarantee to the staff and calculate the sample spray prior to target painting.

Surface preparation:

Thickness of dry coating:

VOC:

~200-300 µm

Date of minimum durability:

2K acrylic Primer, polyester putty: dry sanding with P240-P320 paper, blow with compressed air, degrease. Epoxy Primer: within 12 hours no sanding needed, after 12 hours sand with P320, blow with compressed air, degrease. Steel:

degrease, dry sanding P120, blow with compressed air, degrease. Plastic: clean with CP 015 silicon remover, matt with maroon nonwoven, clean again. Polyester laminates: Degrease, dry sanding P280,

blow with compressed air, degrease.

12 months (in the original unopened package)

2004/42WE/IIB(e) (840) 560