PROFIX



FAST 1 • MEDIUM 2 • FINE 3 • WAX 4

Polishing compounds

FAST compound removes scratches and marks of sanding.

MEDIUM compound removes minor inclusions and scratches e.g. resulting from shading.

FINE compound removes marks of polishing and tarnishing. Perfect for using on freshly applied coat.

WAX fine compound leaves a thin layer enhancing the depth effect and coat color clearness. Polishes do not contain silicone.

Packaging					
Unit	Collective (box)				
1 L	6 pcs				

Destination	Type	Properties				Application Type of Coating			
		Silicone free	Cut*	Gloss*	Color	Fresh OEM Coatings	Fresh Repair Coatings	Aged/weather- worn Coatings	Minimum sanding grit size
Compounding	FAST	✓	5,0	1,5	white		✓	✓	P1000
Polishing	MEDIUM	✓	3,5	3,5	white	✓	✓	✓	P2000
Finishing	FINE	✓	3,0	4,0	white	✓	✓		P2500
Protection	WAX		1,0	5,0	white			✓	

^{*} scale from 1 to 5



24 months (in the original unopened package)



Do not mix different compounds. Before applying another compound it is recommended to thoroughly clean or replace the sponge. The polishing machine should be pressed down sufficiently, particularly when removing polisher rotation marks and/or surface imperfections. Sanding, polishing and finishing are different polishing methods and should be used in the proper order.

The recipe of the product complies with the VOC guidelines. The products supplied by our company are subject to a number of factory tests, so they can meet the highest demands. However, be aware of the individual conditions of storage, preparation and applications that can influence on the effect of varnishing. The guarantee to keep the highest quality of the coating is to use the product only with the products of the Manufacturer and in accordance with the recommendations of the Manufacturer. The Manufacturer does not guarantee performance and compatibility of the Products other than those of the Manufacturer. In order to recognize the guarantee and all claims, the user shall use the technologies and techniques for given Products – according to the technical data sheet and execute the sample spray prior to target painting.